

Zinc-It[®] Instant Cold Galvanize

Zinc-It[®] **Instant Cold Galvanize** is a >93% pure zinc, sacrificial coating that protects ferrous metals from oxidizing. The high purity, zinc-rich formula creates a galvanic barrier between the environment and the base metal to prevent the formation or spread of rust and corrosion.

Electrochemically bonds to metal surfaces.

- Quick drying. Dries to the touch in 15 to 30 minutes. Allows treated parts to be handled quickly
- Protects ferrous metals substantially longer than zinc paints
- Highly resistant to scratching, abrasion, denting, corrosive environments, salt air, moisture and road salts
- **Excellent** weldability

Ideally suited for a variety of environments including marine, utility, refinery, water treatment, chemical processing, pulp & paper, steel manufacturing, general maintenance and repair.

CRC Part #	Container Size	Net Weight	UPC Code
18412	16 oz aerosol	13 oz	0 78254 18412 8
18413	1 gallon can	1 gal	0 78254 18413 5



Your Best Solution™ Customer Service: 800-272-4620 Technical Assistance: 800-521-3168 www.crcindustries.com/ei





CRC Industries is a worldwide leader in the production of specialty chemicals for maintenance and repair professionals serving industrial, electrical, aviation, automotive and marine markets. CRC is ISO 9001:2008 certified and adheres to the strictest guidelines for quality in all facets of research, development and production.



CRC[®], K&W[®], Sta-Lube[®], Marykate[®] and products denoted with [®] and [™] are trademarks of CRC Industries, Inc.



10405-SS PDF



Instant Cold Galvanize

Galvanizador Frío Instantáneo

Actively Fights Corrosion Combate Enérgicamente la Corrosión

DANGER: EXTREMELY RAMABLE HARAFUL OR FATAL FONLOWED VAPOR HARMFUL OUSES SKIN IRRITATION. OWNENTS UNDER PRESSURE VEEP ANAV FROM CHILDREN. WEE ANAV FROM CHILDREN.

PELIGRO: INFLAMABLE: SU NESTION ES PERJUDICIAL O WIRTAL VAPOR DAÑINO. REVINCA IRPITACIÓN CUTÁNEA. CINTENIDO BAJO PRESIÓN. WITENIGA FLERA DEL MUTENIGA FLERA DEL MUTENIGA FLERA DEL MUTENIGA FLERA DEL NESSECTOS MIÑOS.



No. 18412 Net Wt./Peso Net

Net WL/P 13 oz

e in USA







DIRECTIONS: Important – read all directions and cautions before use. Always wear gloves, eye protection and work clothes. Use drop cloths. Product is flammable during dispensing – turn off sources of ignition prior to use.

PREPARATION:

NEW STEEL - Surface must be dry and free of contamination. Remove all weld spatter and grind all rough welds and sharp edges to a smooth contour. For severe exposure (immersion, chemical, etc.) near-white blast clean per SSPC SP 10-63T. For other exposures, blast clean per SSPC SP 6 - 63 to a maximum profile of 1.5 mils.

PREVIOUSLY PAINTED SURFACES - Must be free of oil, grease or other contamination. For best results, spot blast exposed areas to be primed. Power tool brushings may be used for minor touch-up.

APPLICATION: Surface should be dry, above 50°F, and free of rust bloom.

AEROSOL: Shake well until agitator ball is free. Repeat while using. Best results are obtained when sprayed between 50°F-90°F. Spray from 12-15 inches away in light, even coats. Additional coats for heavy film can be applied when first coat is dry. When finished spraying, clean valve by turning can upside down and pressing button until only pressure escapes. If clogging occurs, remove button and clean slot and orifice with fine wire.

BULK: For air atomized spray, reduce 5-10% with Aromatic 100 Solvent, or Xylene for improved atomization. Fluid tips of .070" and air caps delivering 9-10 CFM at 30# PSI are acceptable. A 3/8" to 1/2" material hose is recommended. For airless spray, use .023 - .029 tips with 900 - 1800# fluid pressure. Material should be kept under constant slow speed agitation during use. Double lap all welds, seams, corners and edges to insure proper film thickness. Make even, parallel passes with 50% overlap to provide uniformity.

TYPICAL PROPERTIES Zinc-It® Instant Cold Galvanize			
Type of Film	Dry matte finish		
Dry Film Thickness	1.5- 3 mils		
Corrosion Resistance	500 hrs. ASTM-2247 (humidity) 1000 hrs. ASTM-B117 (salt fog)		
Dry Time	30 minutes for handle		
Cure Time (Full cure)	8 hours		
Recoat	Within 8 hrs		
Aerosol Coverage (dry)	28 to 32 sq. ft @3 mil		
Bulk Coverage (dry)	674 sq. ft @1 mil		
Odor	Solvent		
Appearance	Grey, viscous liquid		
Vapor Density	>air		
Shelf Life	2 years		



Recommend for use on threads, exposed edges, fasteners, conduit, strapping, welds, fencing, railings, grates, electrical poles, breaker panel housings, rain spouts, signs, doors, trailers, waste containers, catwalks, guard rails and more.



Your Best Solution™ Customer Service: 800-272-4620 Technical Assistance: 800-521-3168 www.crcindustries.com/ei





Made in USA

CRC Industries is a worldwide leader in the production of specialty chemicals for maintenance and repair professionals serving industrial, electrical, aviation, automotive and marine markets. CRC is ISO 9001:2008 certified and adheres to the strictest guidelines for quality in all facets of research, development and production.



CRC[®], K&W[®], Sta-Lube[®], Marykate[®] and products denoted with [®] and [™] are trademarks of CRC Industries, Inc.