

## Technical Data Sheet



Eclectic Products, Inc.  
Manufacturing Facility  
101 Dixie Mae Drive  
Pineville, Louisiana  
eclecticproducts.com  
800.349.4667

ISO 9001:2008  
Compliant  
Quality Management  
Systems

Administration Office  
Eugene, Oregon  
eclecticproducts.com  
800.693.4667  
Technical Service  
800.767.4667



109.4 mL (Clear & Black)

Not all styles/sizes/colors available in all  
areas

## AMAZING GOOP

### AUTOMOTIVE ADHESIVE (Clear & Black)

#### PRODUCT DESCRIPTION

AMAZING GOOP AUTOMOTIVE is scientifically formulated to permanently seal a variety of materials used in and around automobiles.

#### WHERE TO USE / APPLICATIONS

Use in and around automobiles to stop tears in vinyl seats, floor mats and convertible tops. AMAZING GOOP AUTOMOTIVE can also coat terminals on batteries.

#### FEATURES AND BENEFITS

**FLEXIBLE** – does not become brittle in cold weather

**CHEMICAL RESISTANT** – safe for applications exposed to dilute acids and dilute caustics

**ABRASION RESISTANT** – great for bonding objects subject to normal wear

**WATERPROOF** – can be submerged in fresh and salt water after complete cure

**PAINTABLE** – paint to match surrounding area or for UV resistance after completely cured

#### TECHNICAL INFORMATION

PROPERTIES	
UNCURED MATERIAL	
Color:	Clear & Black
Solvent:	Perchloroethylene
Non-flammable:	Yes
Density:	11.0 +/- 0.1 lbs/gal
Solids:	30% by weight, 40% by volume
Viscosity:	100,000 cps medium
Tack time:	~ 4 minutes
Set time:	20 minutes*
Full cure time:	Thin film: 24 hours / Thick film: 48-72 hours
Storage:	Product may thicken when stored in colder temperatures but will not freeze. If product thickens from colder temperatures, warm to room temperature before use.
Application Temp:	Ideal application temperature range is 10 to 32 °C.
Freeze/thaw stability:	Stable, allow product to warm to room temperature before using
Shelf life:	2 years (unopened)

\*Depending on material, humidity and temperature.

CURED MATERIAL	
Chemical resistance:	Excellent to water, dilute acids & bases
UV resistance:	None; paint-over for UV resistance
Hardness:	80 Shore A
Dielectric strength:	400V/mil (ASTM D-149); this is the maximum voltage that can be applied to a given material without causing it to break down
Tensile strength:	3500 lb/in <sup>2</sup> (ASTM D-412)
Elongation:	900% (ASTM D-412)
Service temperature:	Cured adhesive can withstand temperatures from -40 to 82 °C intermittently.
Paint-over time:	24 hours

ADHESION TEST – 180° Peel Strength Test - ASTM D 903				
Aluminum	Aluminum	Aluminum	Aluminum	Aluminum
35 pli	35 pli	35 pli	35 pli	35 pli

Avg. Max Load Measured in pli (pounds per linear inch)



## Technical Data Sheet



## AMAZING GOOP

### AUTOMOTIVE ADHESIVE (Clear & Black)

#### EUROPE



59.1 mL

CLEAR & BLACK

*Not all styles/sizes/colors available in all areas*

#### CHEMICALS THAT HAVE LITTLE OR NO EFFECT ON AMAZING GOOP

Acetic acid (5% and 10%)  
Ammonium hydroxide (3.4%)  
Ammonium nitrate (50%)  
Antifreeze  
Beer (3.2% alcohol by volume)  
Boric acid (3.1%)  
Distilled water  
Hydraulic oil  
Lactic acid (3.8%)  
Milk (fresh, tested at 40 °F)  
Motor oil (30w)  
Nitric acid (10% and 20%)  
Oxalic acid (3.1%)  
Phosphoric acid (30% and 60% as P<sub>2</sub>O<sub>5</sub>)  
Potassium hydroxide (3.4%)  
Sodium carbonates (2.7%)  
Sodium chloride (10%)  
Sulfuric acid (3% and 10%)  
Wine (20% alcohol by volume)

AMAZING GOOP exhibits excellent resistance to water, dilute acids and dilute bases. Thin films of GOOP were immersed in various chemicals for two weeks and exhibited weight gains of less than 2% and tensile strength loss of less than 10%. These chemicals are listed on the left. All percentages are given by weight unless otherwise noted.

#### SOLVENTS THAT DISSOLVE AMAZING GOOP

Chevron solvent 1100  
Chlorothane NU  
Cyclohexane  
Gasoline  
Methylene chloride  
Perchloroethylene  
Propyl acetate  
Toluene  
1, 1, 1-Trichloroethane

These are common solvents that dissolve AMAZING GOOP when hardened samples were immersed. The dissolution with these solvents was not instantaneous and therefore does not preclude usage in all cases. Applications were an occasional splash or brief exposure is expected may be acceptable. Test a small area before full use.

#### DIRECTIONS and APPLICATION NOTES

Read directions and test small area before use.

- Step 1 Surface should be clean, dry and free of dirt. For best results, lightly roughen surface before use.
- Step 2 Puncture seal in neck of tube using pointer cap (If tube has a foil seal). Ideal application temperature range is 10 and 32 °C. However, fully cured adhesive can withstand temperatures from -40 to 82 °C intermittently.
- Step 3 Apply directly to surfaces to be bonded or repaired.
- Step 4 Allow repair to cure for 24 hours. Depending on the materials and temperature, maximum strength may not be reached for 48 to 72 hours.
- Step 5 For future easy cap removal, apply a thin coat of petroleum jelly to the threads of the tube before replacing the cap.
- Step 6 Clean uncured adhesive with acetone or citrus-based solvents. Cured material may be removed by cutting or scraping.

Product is paintable and immediately resistant to precipitation upon application.

- Please read all directions before using. Use in well-ventilated area.
- May damage finished surfaces. Avoid such contact until completely dry. Not recommended for use on Styrofoam™, polystyrene, polyethylene, polypropylene or polypropylene plastics, aquariums or refrigeration units and any items that come into contact with food, drinking water or animals.

## Technical Data Sheet

### MIDDLE EAST (ARABIC)



59.1 mL  
CLEAR

*Not all styles/sizes/colors available in all areas*

## AMAZING GOOP

### AUTOMOTIVE ADHESIVE (Clear & Black)

#### HEALTH and SAFETY

This product contains perchloroethylene.

Before working with this product, read and become familiar with information concerning hazards, proper use and handling. SDS's are available online at the following links:

Canada-

English: <http://eclecticproducts.com/downloads/sds-amazing-goop-english-canada.pdf>

French: <http://eclecticproducts.com/downloads/sds-amazing-goop-french-canada.pdf>

Europe-

English (Request SDS) : [sds@eclecticproducts.com](mailto:sds@eclecticproducts.com)

French (Request SDS) : [sds@eclecticproducts.com](mailto:sds@eclecticproducts.com)

Spanish (Request SDS) : [sds@eclecticproducts.com](mailto:sds@eclecticproducts.com)

German (Request SDS) : [sds@eclecticproducts.com](mailto:sds@eclecticproducts.com)

Middle East-

Arabic & English (Request SDS): [sds@eclecticproducts.com](mailto:sds@eclecticproducts.com)

To request a hard copy of the SDS, please send an e-mail to [sds@eclecticproducts.com](mailto:sds@eclecticproducts.com).

#### LIMITED WARRANTY

The product is warranted against any defect in materials or workmanship under normal use for a period of 180 days after the date of purchase. The product is also warranted under any implied warranties provided under applicable state law, including, without limitation, the implied warranty of merchantability and the implied warranty of fitness for a particular purpose, for a period of 180 days after the date of purchase. This warranty covers only the original buyer of the product. For warranty service, the buyer should contact the store where the product was purchased, or write Eclectic Products, Inc., P.O. Box 4450, Pineville LA 71361 or call 800.767.4667. This warranty gives you specific legal rights, and you also have other rights, which vary from state to state.