

Technical Data Sheet



Eclectic Products, Inc.
 Manufacturing Facility
 101 Dixie Mae Drive
 Pineville, Louisiana
 eclecticproducts.com
 800.349.4667

ISO 9001:2008
 Compliant
 Quality Management
 Systems

Administration Office
 Eugene, Oregon
 eclecticproducts.com
 800.693.4667
 Technical Service
 800.767.4667



109.4 mL

Not all styles/sizes/colors available in all areas

AMAZING GOOP PLUMBING ADHESIVE

PRODUCT DESCRIPTION

AMAZING GOOP PLUMBING is a versatile and permanent contact adhesive and sealant that great for just about any do-it-yourself plumbing project. Dries clear. Waterproof. Paintable.

WHERE TO USE / APPLICATIONS

Use to seal everything around the house from sink traps and porcelain fixtures to pool or shower tiles and down spouts. Adheres to glass, plastic, metal, ABS, PVC, copper, vinyl, rubber, brick, wood and more!

FEATURES AND BENEFITS

FLEXIBLE – does not become brittle in cold weather

CHEMICAL RESISTANT – safe for applications exposed to dilute acids and dilute caustics

ABRASION RESISTANT – great for bonding objects subject to normal wear

WATERPROOF – can be submerged in fresh and salt water after complete cure

PAINTABLE – paint to match surrounding area or for UV resistance after completely cured

TECHNICAL INFORMATION

PROPERTIES	
UNCURED MATERIAL	
Color:	Clear
Solvent:	Perchloroethylene
Non-flammable:	Yes
Density:	11.0 +/- 0.1 lbs/gal
Solids:	30% by weight, 40% by volume
Viscosity:	100,000 cps
Tack time:	~ 4 minutes
Set time:	20 minutes*
Full cure time:	Thin film: 24 hours / Thick film: 48-72 hours
Storage:	Product may thicken when stored in colder temperatures but will not freeze. If product thickens from colder temperatures, warm to room temperature before use.
Application Temp:	Ideal application temperature range is 10 to 32 °C.
Freeze/thaw stability:	Stable, allow product to warm to room temperature before using
Shelf life:	2 years (unopened)

*Depending on material, humidity and temperature.

CURED MATERIAL	
Chemical resistance:	Excellent to water, dilute acids & bases
UV resistance:	None; paint-over for UV resistance
Hardness:	80 Shore A
Dielectric strength:	400V/mil (ASTM D-149); this is the maximum voltage that can be applied to a given material without causing it to break down
Tensile strength:	3500 lb/in ² (ASTM D-412)
Elongation:	900% (ASTM D-412)
Service temperature:	Cured adhesive can withstand temperatures from -40 to 82 °C intermittently.
Paint-over time:	24 hours

Technical Data Sheet



AMAZING GOOP PLUMBING ADHESIVE

EUROPE



59.1 mL

Not all styles/sizes/colors available in all areas

MIDDLE EAST (ARABIC)



59.1 mL

Not all styles/sizes/colors available in all areas

ADHESION TEST – 180° Peel Strength Test - ASTM D 903				
Aluminum	Birch (wood)	Glass	PVC	Steel
35 pli	40 pli	34 pli	38 pli	45 pli

Avg. Max Load Measured in pli (pounds per linear inch)

CHEMICALS THAT HAVE LITTLE OR NO EFFECT ON AMAZING GOOP

Acetic acid (5% and 10%)
 Ammonium hydroxide (3.4%)
 Ammonium nitrate (50%)
 Antifreeze
 Beer (3.2% alcohol by volume)
 Boric acid (3.1%)
 Distilled water
 Hydraulic oil
 Lactic acid (3.8%)
 Milk (fresh, tested at 40 °F)
 Motor oil (30w)
 Nitric acid (10% and 20%)
 Oxalic acid (3.1%)
 Phosphoric acid (30% and 60% as P₂O₅)
 Potassium hydroxide (3.4%)
 Sodium carbonates (2.7%)
 Sodium chloride (10%)
 Sulfuric acid (3% and 10%)
 Wine (20% alcohol by volume)

AMAZING GOOP exhibits excellent resistance to water, dilute acids and dilute bases. Thin films of GOOP were immersed in various chemicals for two weeks and exhibited weight gains of less than 2% and tensile strength loss of less than 10%. These chemicals are listed on the left. All percentages are given by weight unless otherwise noted.

SOLVENTS THAT DISSOLVE AMAZING GOOP

Chevron solvent 1100
 Chlorothane NU
 Cyclohexane
 Gasoline
 Methylene chloride
 Perchloroethylene
 Propyl acetate
 Toluene
 1, 1, 1-Trichloroethane

These are common solvents that dissolve AMAZING GOOP when hardened samples were immersed. The dissolution with these solvents was not instantaneous and therefore does not preclude usage in all cases. Applications were an occasional splash or brief exposure is expected may be acceptable. Test a small area before full use.

DIRECTIONS and APPLICATION NOTES

Read directions and test small area before use.

- Step 1 Surface should be clean, dry and free of dirt. For best results, lightly roughen surface before use.
- Step 2 Puncture seal in neck of tube using pointer cap (If tube has a foil seal). Ideal application temperature range is 10 and 32 °C. However, fully cured adhesive can withstand temperatures from -40 to 82 °C intermittently.
- Step 3 Apply directly to surfaces to be bonded or repaired.
- Step 4 Allow repair to cure for 24 hours. Depending on the materials and temperature, maximum strength may not be reached for 48 to 72 hours.
- Step 5 For future easy cap removal, apply a thin coat of petroleum jelly to the threads of the tube before replacing the cap.
- Step 6 Clean uncured adhesive with acetone or citrus-based solvents. Cured material may be removed by cutting or scraping.

Product is paintable and immediately resistant to precipitation upon application.

- Please read all directions before using. Use in well-ventilated area.
- May damage finished surfaces. Avoid such contact until completely dry. Not recommended for use on Styrofoam™, polystyrene, polyethylene, polypropylene or polypropylene plastics, aquariums or refrigeration units and any items that come into contact with food, drinking water or animals.

AMAZING GOOP

PLUMBING ADHESIVE

HEALTH and SAFETY

This product contains perchloroethylene.

Before working with this product, read and become familiar with information concerning hazards, proper use and handling. SDS's are available online at the following links:

Canada-

English: <http://eclecticproducts.com/downloads/sds-amazing-goop-english-canada.pdf>

French: <http://eclecticproducts.com/downloads/sds-amazing-goop-french-canada.pdf>

Europe-

English (Request SDS): sds@eclecticproducts.com

French (Request SDS): sds@eclecticproducts.com

Spanish (Request SDS): sds@eclecticproducts.com

German (Request SDS): sds@eclecticproducts.com

Middle East-

Arabic & English (Request SDS): sds@eclecticproducts.com

To request a hard copy of the SDS, please send an e-mail to sds@eclecticproducts.com.

LIMITED WARRANTY

The product is warranted against any defect in materials or workmanship under normal use for a period of 180 days after the date of purchase. The product is also warranted under any implied warranties provided under applicable state law, including, without limitation, the implied warranty of merchantability and the implied warranty of fitness for a particular purpose, for a period of 180 days after the date of purchase. This warranty covers only the original buyer of the product. For warranty service, the buyer should contact the store where the product was purchased, or write Eclectic Products, Inc., P.O. Box 4450, Pineville LA 71361 or call 800.767.4667. This warranty gives you specific legal rights, and you also have other rights, which vary from state to state.