

**GENERAL DESCRIPTION**

Glidden One Coat Interior Paint + Primer is a super-premium paint with one coat coverage* to save you time and money. It has exceptional hide and stain blocking properties to hide common stains and make your walls beautiful. It has excellent scrubability so it can stand up to frequent cleanings. Featuring a hand selected palette of over 300 of our most popular colors, one easy coat is all you need!

***Learn more at glidden.com.onecoat. One coat coverage only when tinted to colors specified for *Glidden One Coat Interior Paints*.**

RECOMMENDED SUBSTRATES

Concrete/Masonry	Gypsum Wallboard-Drywall
Concrete Block (CMU)	Plaster
Ferrous Metal	Wood

FEATURES / BENEFITS

One Coat Coverage*
Exceptional Hide & Stain Blocking
Excellent Scrubbability
100% Acrylic
Low Odor / Low VOC

***Learn more at glidden.com.onecoat. One coat coverage only when tinted to colors specified for *Glidden One Coat Interior Paints*.**

CONFORMANCE STANDARDS

VOC compliant in all regulated areas

TINTING AND BASE INFORMATION

GLOIN30WB	White & Pastel Base
GLOIN30WH	Ready-Mix White
GLOIN30MB	Midtone Base*
GLOIN30DB	Ultra Deep Base*

*Must be tinted before use.

Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

PACKAGING

Quart (946 mL)
1-Gallon (3.78 L)

Not all products available in all sizes.

PRODUCT DATA

PRODUCT TYPE:	100% Acrylic Latex
SHEEN:	Semi-Gloss: 40-60 @60°
VOLUME SOLIDS*:	41% +/- 2%
WEIGHT SOLIDS*:	55% +/- 2%
WEIGHT/GALLON*:	10.8 lbs. (4.9 kg) +/- 0.2 lbs. (91 g)
VOC*:	<50 g/L (0.4 lbs./gal.)

*Product data calculated on product GLOIN30WB.

COVERAGE: Up to 400 sq. ft. (37.2 sq. meters) per U.S. Gallon (3.78L) on smooth, nonporous surfaces.

Wet Film Thickness:	4.0 mils
Wet Microns:	102
Dry Film Thickness:	1.6 mils
Dry Microns:	41

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing. Some colors, drastic color changes, or porous substrates may require more than one coat to achieve a uniform finish.

DRYING TIME:	Dry time @ 77°F (25°C); 50% relative humidity.
To Touch:	1 hour
To Recoat:	4 hours
To Full Cure:	30 days

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement.

CLEANUP: Clean tools with warm, soapy water.

WASHING INSTRUCTIONS: Wait at least 30 days after painting before cleaning the surface with a non-abrasive mild cleaner.

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 200°F (93°C)

LIMITATIONS OF USE

FOR INTERIOR USE ONLY. Apply paint only when air, product and surface temperatures are between 50°F (10°C) and 90°F (32°C).

Not recommended for use on steps or floors.

PROTECT FROM FREEZING.

GENERAL SURFACE PREPARATION

Surface must be clean and dry. Remove all loose and peeling paint, dirt, mildew, grease, oil, chalk, rust, and any other surface contaminants. Putty all nail holes, and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. When applied to an uncoated substrate, two coats are required, with the first coat acting as the primer. The appropriate specialty primer is recommended for special substrates such as tannin staining wood, chalky masonry, and bare metal.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. In Canada contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

CONCRETE, MASONRY and PLASTER: New concrete, masonry and plaster should cure for at least 30 days and preferably 90 days prior to painting. The pH of the substrate must be less than 10.

CONCRETE BLOCK (CMU): Mortar should cure for at least 30 days and preferably 90 days prior to painting. Fill block with an appropriate block filler.

FERROUS METAL: The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed.

GYPSUM WALLBOARD-DRYWALL: Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust prior to painting the substrate.

WOOD: Unpainted wood or wood in poor condition should be sanded smooth and wiped clean. Any knots or resinous areas must be primed before painting. Countersink all nails, putty flush with surface, then paint.

APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

Application Equipment: Apply with a high quality brush, roller, paint pad, or by spray equipment. Where necessary, apply a second coat and allow each coat to dry thoroughly before applying the next coat.

Airless Spray: Minimum pressure 2000 psi, tip 0.015" - 0.021". Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brush: Polyester/Nylon Brush

Roller: 3/8" - 1/2" nap roller cover

Thinning: No thinning required.

Permissible temperatures during application:

Material: 50 to 90°F 10 to 32°C Ambient: 50 to 100°F 10 to 38°C Substrate: 50 to 100°F 10 to 38°C

PRECAUTIONS

WARNING! HARMFUL IF INHALED. HARMFUL IF SWALLOWED. Sanding and grinding dusts may be harmful if inhaled. Do not breathe vapor or mist. Do not swallow. Keep container tightly closed and sealed until ready for use. Wash thoroughly after handling. Provide fresh air ventilation during and after application and drying. Avoid the inhalation of dust, particulates, spray or mist arising from the application of this preparation. Use personal protective equipment as required. **Note: These warnings encompass the product series. Prior to use, read and follow product-specific SDS and label information. FIRST AID:** If swallowed, rinse mouth with water (only if the person is conscious). Call physician immediately. Do not induce vomiting unless directed to do so by medical personnel. If in eyes, rinse with water for 15 minutes. Check for and remove any contact lenses. If on skin, rinse well with water. Wash with soap and water. Get medical attention if irritation develops. If inhaled, remove to fresh air. If experiencing respiratory symptoms call a POISON CENTER or doctor/physician. Keep out of the reach of children. For workplace use, an SDS is available from your retailer or by calling (412) 492-5555. EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.).

© 2018 PPG Industries, Inc., All Rights Reserved. *Glidden One Coat* and the *Glidden Logo* are trademarks of the PPG Group of Companies. The *PPG Logo* is a registered trademark of PPG Industries Ohio, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Industries, Inc.
Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.glidden.com

Technical Services
1-800-441-9695
1-888-807-5123 fax

Architect/Specifier
1-888-PPG-IDEA

PPG Architectural Coatings Canada Inc.
2505, rue de la Metropole
Longueuil (Quebec) Canada J4G 1E5

GLOIN30WB - 1/2018

