



Architectural Coatings

GENERAL DESCRIPTION

Glidden Grab-N-Go Farm & Implement Interior/Exterior High Gloss is ideal for use on properly prepared interior and exterior safety equipment and piping, farm implements, machinery, and tank exteriors. It may also be used as a trim enamel. It provides excellent protection to metal surfaces, masonry, wood and wallboard. Note: Alkyd or oil-based enamels may yellow over time in the absence of light, especially sunlight.

RECOMMENDED SUBSTRATES

Concrete/Masonry
Ferrous Metal
Gypsum Wallboard-Drywall
Plaster
Wood

FEATURES / BENEFITS

Durable & Scrubbable
Alkyd Enamel
For use on: Machinery, Equipment, Piping, Tanks, Masonry, Wood,
Other Metal Surfaces

TINTING AND BASE INFORMATION

GLFIIIE50AL	Aluminum
GLFIIIE50BL	Black
GLFIIIE50BR	Brown
GLFIIIE50GR	Medium Green
GLFIIIE50MG	Machine Gray
GLFIIIE50OR	Safety Orange
GLFIIIE50RE	Safety Red
GLFIIIE50WH	White
GLFIIIE50YE	Safety Yellow

Ready-Mixed Paint, DO NOT TINT.

PACKAGING

Quart (946 mL)
1-Gallon (3.78 L)

GLIDDEN® Grab-N-Go Farm & Implement Interior/Exterior High Gloss

PRODUCT DATA

PRODUCT TYPE:	Alkyd
SHEEN:	Gloss, 85 minimum @ 60°
VOLUME SOLIDS*:	45% +/- 2%
WEIGHT SOLIDS*:	61% +/- 2%
WEIGHT/GALLON*:	9.3 lbs. (4.2 kg) +/- 0.2 lbs. (91 g)
VOC*:	<450 g/L (3.8 lbs./gal.)

*Product data calculated on product GLFIIIE50WH.

COVERAGE: Approximately 300-400 sq. ft. (28-37 sq. meters) per US gallon (3.78 Liters) on primed, smooth, nonporous surfaces.

Wet Film Thickness:	4.0-5.3 mils
Wet Microns:	102-135
Dry Film Thickness:	1.8-2.4 mils
Dry Microns:	46-61

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing. Some colors, drastic color changes, or porous substrates may require more than one coat to achieve a uniform finish.

DRYING TIME: Dry time @77°F (25°C) & 50% relative humidity.

To Touch:	5 hours
To Handle:	8 hours
To Recoat:	24 hours

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement.

CLEANUP: Clean tools with mineral spirits or VM&P Naphtha.

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: 108°F (42°C)

LIMITATIONS OF USE

Do not apply in damp weather or when air, product and surface temperatures are below 40°F (4°C). Avoid painting in direct sunlight or on hot surfaces. Surfaces coated with this product may become slippery when wet. For additional slip resistance in areas of pedestrian traffic, add one pound per gallon of coarse pumice or other texturing material.

USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our website or by calling 1-800-441-9695.

Read Label and Safety Data Sheet Prior to Use. See other cautions on last page.

GLFIIIE50WH Series

GENERAL SURFACE PREPARATION

Surface must be sound, clean, and dry. Remove all loose, peeling paint, dirt, grease, mildew, form release agents, curing compounds, efflorescence, and any other foreign surface contaminants. Sand all glossy, rough and patched surfaces. Prime all new wood, drywall, concrete, plaster, masonry, metal, and porous surfaces with an appropriate primer

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

CONCRETE/MASONRY: New concrete and masonry should cure for at least 30 days and preferably 90 days prior to priming. The pH of the substrate must be less than 10 before priming with an alkali resistant primer.

FERROUS METAL: The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, then primed with a metal primer.

GYPSUM WALLBOARD-DRYWALL: Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust, then prime prior to painting the substrate.

PLASTER: Plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming with an alkali resistant primer.

WOOD: Countersink all nails, putty flush with surface. Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be primed before painting.

APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, intermix to ensure color uniformity.

Application Equipment: Apply with a high quality brush, roller, paint pad or by spray equipment. Two coats will provide best durability and uniformity.

Airless Spray: For airless spray application, use tip size .013" and adjust pressure as needed. Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brush: Natural Bristle Brush

Roller: 3/16" to 3/8" nap roller cover

Thinning: DO NOT THIN

Permissible temperatures during application:

Material: 40 to 90°F 4 to 32°C

Ambient: 40 to 90°F 4 to 32°C

Substrate: 40 to 90°F 4 to 32°C

PRECAUTIONS

DANGER! FLAMMABLE LIQUID AND VAPOR. HARMFUL IF ABSORBED THROUGH SKIN. HARMFUL IF INHALED. HARMFUL OR FATAL IF SWALLOWED. CAUSES RESPIRATORY TRACT, EYE AND SKIN IRRITATION. Sanding and grinding dusts may be harmful if inhaled.

Inhalation of high concentrations of vapor may affect the central nervous system. Repeated exposure to high vapor concentrations may cause irritation of the respiratory system and permanent brain and nervous system damage. High vapor concentrations can cause headaches, dizziness, drowsiness and nausea and may lead to unconsciousness. The product may not be stable under certain conditions of storage or use: high temperature/pressure hazard. Can enter lungs and cause damage. Keep away from heat and flame. Do not breathe vapor or mist. Do not swallow. Do not get on skin or clothing. Avoid contact with eyes. Keep container tightly closed and sealed until ready for use. Wash thoroughly after handling. Provide fresh air ventilation during and after application and drying. Avoid the inhalation of dust, particulates, spray or mist arising from the application of this preparation. Use personal protective equipment as required. **DANGER - RAGS, STEEL WOOL OR WASTE SOAKED WITH FARM & IMPLEMENT MAY SPONTANEOUSLY CATCH FIRE IF IMPROPERLY DISCARDED. IMMEDIATELY AFTER EACH USE, PLACE RAGS, STEEL WOOL OR WASTE IN A SEALED WATER-FILLED METAL CONTAINER. Note: These warnings encompass the product series. Prior to use, read and follow product-specific SDS and label information. FIRST AID:** If swallowed, rinse mouth with water (only if the person is conscious). Call physician immediately. Do not induce vomiting unless directed to do so by medical personnel. If in eyes, rinse with water for 15 minutes. Check for and remove any contact lenses. If on skin, rinse well with water. Wash with soap and water. Get medical attention if irritation develops. If inhaled, remove to fresh air. If experiencing respiratory symptoms call a POISON CENTER or doctor/physician. Keep out of the reach of children. For workplace use, an SDS is available from your retailer or by calling (412) 492-5555. EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.).

© 2018 PPG Industries, Inc. All Rights Reserved. The PPG Logo is a registered trademark of PPG Industries Ohio, Inc. Glidden is a registered trademark and the Glidden Logo is a trademark of the PPG Group of Companies.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-454-3336.



PPG Industries, Inc.
Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.glidden.com

Technical Services
1-800-GLIDDEN

GLFIIIE50WH - 2/2018