

Majic Diamond Hard Tractor, Truck, & Auto Acrylic Enamel

8-4900 series

DESCRIPTION

A durable, heavy duty acrylic enamel specially formulated for excellent adhesion and resistance to weathering and corrosion. It can be applied with brush or spray and dries quickly to a high gloss finish. Great gloss retention, durability and a fast dry time is achieved without adding a catalyst.



FEATURES

- A water-based acrylic enamel.
- For use on metal, properly prepared steel, previously coated and primed substrates.
- Ideal for use on equipment, machinery, and any project where a fast dry time is required.
- Great gloss retention, durability and a fast dry time is achieved without adding a Catalyst.

VOC / MIR (sprays)

250 gm/l (2.09 lbs/gal)

NET WEIGHT

8.65~10.07 lbs

AVAILABLE SIZES

Quart, Gallon

SHIPPING WT

2-gal case/22 lbs
4-qt case/11 lbs

AVAILABLE COLORS

8-4957 J.D. Yellow, 8-4966 J.D Green, 8-4972 I.H. Red, 8-4990 Gloss White, 8-4994 Gloss Black

SHIPPING RESTRICTION

None

PRODUCT STATISTICS

DRYTIME-TOUCH 1.5 hrs	DRYTIME-RECOAT 3 hours	WET/ FILM THK 3 mils	FILM THK /DRY: 1 mil	FINISH High Gloss	GLOSS 80+ @ 60°
FLASHPOINT > 200° F	COVERAGE ~300-400 sq ft/ gal	VISCOSITY 80-88	VEHICLE ACRYLIC	SOLVENT Water	

SURFACE PREP

BARE METAL: Remove all rust scale with wire brush or sander. Remove oil and grease. Prime with Majic Tractor, Truck & Auto Acrylic Gray Primer. **PAINTED METAL:** Remove loose or peeling paint and rust scale with wire brush or sander. Remove oil and grease. Prime any bare metal. **PAINTED SURFACES:** (General) Make sure surface is clean, dry, free of loose paint, dirt, wax, grease, etc. Sand glossy areas. Rinse surface thoroughly with fresh water and allow to fully dry. All surfaces must be dry at time of application.

APPLICATION

Stir thoroughly. Apply with a high quality brush or by spray equipment at a film thickness of 2 mil. Where necessary apply a second coat and allow each coat to dry thoroughly before applying the next coat. Do not apply if air or surface temperature is below 50° F or above 95° F or in direct sunlight. Do not apply to hot surfaces above 200° F. The relative humidity should not be greater than 85%. Extremely high or low relative humidity can effect dry time and the final gloss of the coating. On unpainted surfaces, apply two coats for best result, sanding lightly between coats. To spray, reduce with 5-10% of fresh clean water by volume as needed. Allow at least 24 hours after the final coat, before subjecting equipment to heavy use.

WARNING

If you scrape, sand or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Yenkin-Majestic Paint Corp. 1920 Leonard Ave. Columbus, OH 43219 Ph: (800) 848-1898 Fx: (614) 258-3062

The information and specifications stated here are for the material currently offered, are subject to change without prior notice, and due to variations in user handling and application methods should not be relied upon without testing under user conditions. The supplier makes no warranty of any kind, express or implied, concerning this product or its use either singly or in combination with other substances. User assumes all risks incident to its use. User must communicate to employees and customers all warnings that relate to the potential exposure to this product. The user assures that workplace and disposal practices are in compliance with laws, regulations and ordinances. **ALL WARRANTIES, INCLUDING WARRANTIES OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE EXPRESSLY EXCLUDED. IN NO EVENT SHALL THE SUPPLIER BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**

REVISED DATE 8/22/2014