

WOOD & DECK

WDA - CLEANER / WDB - BRIGHTENER

MESSMER'S WOOD & DECK CLEANER (Part A) and WOOD & DECK BRIGHTENER (Part B) are powder concentrates designed to prepare exterior wood for staining. WOOD & DECK CLEANER removes dirt and gray from exterior wood surfaces. WOOD & DECK BRIGHTENER brightens wood surfaces after cleaning or stripping, enhances wood grain appearances, and restores wood's pH.

PRODUCT TYPE

Powder concentrates, to be mixed with water before use WDA Cleaner contains Sodium Percarbonate WDB Brightener contains Oxalic Acid

APPEARANCE

White granular (WDA) or crystalline (WDB) powder

VOC CONTENT

WDA 0 grams / liter WDB 0 grams / liter

SOLIDS BY VOLUME AND WEIGHT

WDA 100% WDB 100%

COVERAGE

Up to 600 square feet per pound when mixed with water. Tougher jobs may require a second application, or more concentrated mixing.

DRY TIME

Allow at least 24-48 hours dry time before staining after cleaning and/or brightening with WDA or WDB.

WDB may be used immediately after rinsing WDA

APPLY WITH

Garden sprayer, mop or plastic bristle brush

PACKAGING

One pound jars

INSTRUCTIONS

SURFACE PREPARATION

Remove dirt and debris from wood surfaces before proceeding

SPECIAL INSTRUCTIONS

Dissolve approximately 1/3 cup of powder in one gallon of hot water and mix well. Mix in a plastic bucket. Once mixed, products should be used promptly.

WDA Cleaner

Mix according to label directions. Apply with a garden sprayer, mop or brush. Allow product to soak on wood briefly. Agitate with a stiff brush or push broom. Rinse thoroughly with clean water.

WDB Brightener

Mix according to label directions. Apply to cleaned and rinsed wood. Allow product to dwell on wood surface for 10-15 minutes, then rinse thoroughly with clean water. After application and rinsing, immediately flood surrounding vegetation with generous amounts of water.

CLEANUP

Clean tools and brushes with water

PRECAUTIONS

Keep out of the reach of children. Mix in plastic containers. To prevent corrosion do not allow products to dwell on unpainted aluminum or steel. Follow all label directions.