

TECHNICAL DATA SHEET

OLD MASTERS® WOOD CONDITIONER

AVAILABLE SIZES: Quart (04) and Gallon (01)

PRODUCT CODES: 50104 quart

50101 gallon

PRODUCT DESCRIPTION: Old Masters® Wood Conditioner is a pre-stain, clear wood sealer which enables uniform stain

application on soft woods, such as fir, pine or hemlock. Generally, softer woods accept stain in various degrees creating an uneven appearance; Wood Conditioner helps to eliminate this variance. This product can be applied under oil or water based stains, but stain must be applied over Wood Conditioner within 2 hours. Ideal for use on soft woods which are being stained with

or adjacent to hardwoods.

SURFACE PREPARATION: All surfaces must be clean, dry and free from dirt, wax or grease. If persistent wax exists, remove with fine steel wool saturated with paint thinner or alcohol. This product does not take the place of sanding sealer in its usage. It is a pre-stain treatment only.

> Bare Wood: Sand the wood thoroughly with medium grit sandpaper and progress to fine grit sandpaper. Always sand in the direction of the wood grain. Sand smooth and remove all dust.

> Previously Finished Surfaces: Strip the surface completely down to bare wood with paint or varnish remover, making sure all previous finishes are removed. Surface must be sanded smooth. Remove all dust.dry. Remove all dust prior to application.

> Note: DO NOT use a tack rag to remove dust, as it may leave a residue that will interfere with adhesion.

> WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION: Stir product thoroughly with a circular, lifting motion to disperse contents evenly.

- 1. Apply with a polyester or nylon brush. Ensure entire surface has been coated.
- 2. Allow Stain Controller to penetrate surface 5 to 15 minutes. Remover excess by wiping with a clean rag. Do not leave a surface film; work in a small area so the product can not set up.
- 3. Do not allow to dry thoroughly. Stain must be applied over Wood Conditioner within 2 hours.

Note: Color depth may vary according to type of wood, stain and application technique. To assure that your finished color is accurate, we highly recommend you test your technique, wood stain and wood type before you start your project.

THINNING: Do not thin. Use as packaged.

COVERAGE: Approximately 400 to 500 square feet per gallon depending upon method of application, type

and porosity of wood.



TECHNICAL DATA SHEET

OLD MASTERS® WOOD CONDITIONER

DRYING TIME: Do not allow to dry thoroughly. Stain must be applied over Wood Conditioner within 2 hours.

CLEAN UP: Using a cleaning solvent, such as paint thinner or mineral spirits, is recommended for cleanup.

The use of paint thinners or mineral spirits may violate VOC compliancy in your area. Check with

your local government agencies to ensure proper compliancy.

To avoid spontaneous combustion during temporary storage, soak soiled rags and waste imme-

diately after use in a water-filled, closed metal container.

MAX VOC: 650 grams/liter (5.4 lbs/gal)

TECHNICAL DATA

SOLIDS BY WEIGHT: 20% FLASH POINT: 86°F Tag Closed Cup

SOLIDS BY VOLUME: 16 to 17% VISCOSITY AT 77°: 30 sec. #2 Ford Cup

V.O.C.: 650 grams/liter AVERAGE DRY TIME

@ 70°F AND 50% R.H.: Approximately 1 to 2 hours

COVERAGE @ Mil DFT: 260 sq. ft. per gal.

VEHICLE: Oil

Not applicable

COVERAGE @

RECOMMENDED DFT Not applicable RECOMMENDED Thinning not recommended. Use

THINNER: as packaged.

THEORETICAL

DFT PER COAT:

WEIGHT PER GALLON: 6.7 to 6.8 lbs.