

UNIT SIZES	UNITS P/CASE	UPC NO.	SHIPPING WEIGHT
2 OZ.	12 / 48	027776	3 lb./13 lb.
1/2 LB.	12	087770	9 lb.
1 LB.	12	167779	17 lb.
4 LB.	2	647776	11 lb.
8 LB.	1	128770	11 lb.
90 LB.	(2) 5 gal.	909072	90 lb.

UPC MFG. PREFIX NUMBER: 0 54983

PHYSICAL PROPERTIES

COLOR (component A)	Light Grey
COLOR (component B)	Black
COLOR (Mixed)	Dark Grey
WORKING TIME (70°F)	60 min. max.
TACK FREE CURE TIME	160 min.
CURE FOR SERVICE	Overnight
MAXIMUM CURE	1-2 Weeks
GARDNERS IMPACT RESISTANCE	160 in./lb.
ELONGATION	2%
CONDUCTION (Electric)	Non Conductive
THERMAL SHOCK	Excellent
TOXICITY (see caution below)	Cured PC-7® Non Toxic
HEAT RANGE (Temp.)	-20°F to 200°F

TEST METHOD	VALUE
TENSILE SHEAR STRENGTH	ASTM D 1002 2,150 PSI
COMPRESSIVE YIELD	ASTM D 695 4,245 PSI
FLEXURAL STRENGTH	ASTM C 580 2,920 PSI
WATER ABSORPTION	ASTM C 413 .44%
WEIGHT (specific gravity)	ASTM D 792 1.16g/cm ³ .671oz/in ³
HARDNESS SHORED	ASTM D 2240 76 (1wk)
HEAT DEFLECTION	ASTM D 648 120°F

CAUTION:

CONTAINS EPOXY RESIN AND POLYAMIDE HARDENER. CAN BE A SKIN IRRITANT. KEEP AWAY FROM EYES AND SKIN. WASH WITH SOAP AND WATER. IN CASE OF EYE CONTACT, FLUSH EYES FOR 15 MINUTES AND GET MEDICAL ATTENTION. CALL DOCTOR IF SWALLOWED. DO NOT INDUCE VOMITING. WEAR APPROVED NIOSH MASK WHEN SANDING. **KEEP AWAY FROM CHILDREN AND PETS.**

Standard Data Sheet (SDS) available upon request.

PC-FIX YOUR THINGS™ with PC-Products®

PC-7®
Epoxy Paste

PC-7®
Pasta Epóxica

PC-7®
Pâte Époxyde

Directions:

Using separate knives (remove amount needed from cans), mix equal parts of A (lt. gray) and B (black) until uniform in color. Surfaces to be bonded must be free of dirt, oil, rust, etc. At 21°C (70°F) PC-7® will remain workable for one hour and cures for service overnight. Do not subject to sustained heat in excess of 93°C (200°F).

Mixing Tips:

In cool temperatures, place PC-7® containers near heat to insure easier mixing. Any smooth surface is good for mixing on. Simple 1:1 mix.

Since mixing and use of this product is beyond our control we accept no liability other than refund or replacement due to product defect only.

*** Cure is faster at higher temperatures, and slower at cooler temperatures.**

The Powerhouse of Repair Products.

Instrucciones:

Con ayuda de cuchillas separadas (extraiga de las latas la cantidad necesaria), mezcle partes iguales de A (gris claro) y B (negro) hasta obtener un color uniforme. Las superficies a adherirse deben estar exentas de suciedad, aceite, óxido, etc. A 21°C (70°F) PC-11® Permanecerá malleable durante 1 hora y alcanzará el curado de servicio en 12 horas. No exponga el producto a un calor constante superior a 93°C (200°F).

Consejos Para el Mezclado:

En lugares con temperaturas frías, coloque los contenedores de PC-7® cerca del calor para asegurar una mezcla. Mezcla fácil en proporción 1:1.

Dado que la mezcla y el uso de este producto están fuera de nuestro control renunciamos a cualquier responsabilidad que no sea el reembolso del importe de compra o el reemplazo del producto debido a defectos en el producto mismo.

***La curación es más rápida en temperaturas más altas, y más lento en temperaturas más frescas.**

El Principal Fabricante de Productos Para Reparaciones.

Mode D'emploi:

Avec des couteaux distincts (retirez la quantité nécessaire des pots), mélangez des quantités égales de A (gris clair) et de B (noir) jusqu'à obtenir une couleur uniforme. Les surfaces à coller doivent être dépourvues de saleté, d'huile, de rouille, etc. A 21°C, PC-11® reste malleable pendant une heure et durcit en une nuit. Ne le soumettez pas à une chaleur soutenue de plus de 93°C.

Conseils de Mélange:

Pat temps frais, placez les recipients près d'une source de chaleur pour faciliter le mélange. Toutes les surfaces lisses conviennent pour le mélange. Mélangez simplement 1:1.

Comme le mélange et l'emploi de ce produit sont hors de notre contrôle, nous n'acceptons aucune responsabilité autre que le remboursement ou le remplacement dû au défaut du produit uniquement.

***Le traitement est plus rapide à températures élevées, et plus lent aux températures plus fraîches.**

La Centrale des Produits de Réparation.

PC-Products® - Protective Coating Co. (Since 1954)

221 South Third Street, Allentown, PA · USA 18102

Phone (610) 432-3543 · Fax (610) 432-5043 · Toll Free 1-800-220-2103

web site: www.pcepoxy.com · e-mail: jack@pcepoxy.com

MADE IN AMERICA

