

THERMO-LUBE PRODUCT No. 1905

PRODUCT DESCRIPTION

QUIKRETE® Thermo-Lube (#1905) is an accelerating admixture liquid for concrete and mortar in cold weather, hastening the hydration of Portland cement which enables the cement to harden before freezing.

PRODUCT USE

QUIKRETE® Thermo-Lube is used as an additive to concrete and mortar to help accelerate the set and reduce the time that the fresh concrete needs to be protected from freezing. It is also excellent as a "wetting" agent or a lubricant to allow for more workability. QUIKRETE® Thermo-Lube meets ASTM specification C 494 for Type C Accelerating Admixtures as shown in Table 1B. Early strengths are also enhanced by the addition of QUIKRETE® Thermo-Lube without adversely affecting later strengths. It also imparts excellent workability to all concrete and mortar mixes at any temperature.

SIZES

• QUIKRETE® Thermo-Lube is available in 1 gallon (3.8 L), 5 gallon (19 L), and 55 gallon (208 L) sizes

TECHNICAL DATA

APPLICABLE STANDARDS

ASTM International

• ASTM C494/C494m Standard Specification for Chemical Admixtures for Concrete

RATE OF APPLICATION

• For best results, use within the recommended dosage range shown in Table 1A. For maximum acceleration use the highest recommended dosage. Do not under any circumstances use more than the maximum recommended dosage.

Table 1A: Recommended Dosage Range:

rabio ir ii rioddiiiiidda 2 ddaga riai gar		
94# (42.6 kg) bag Portland Cement	20-78 fl. oz. (590 - 2310 ml)	
80# (36.3 kg) bag Concrete Mix	3- 10 fl.oz. (90- 300 ml)	
80# (36.3 kg) bag Mortar Mix	2 - 8 fl.oz. (60 - 240 ml)	
60# (27.2 kg) bag Concrete Mix	2 - 8 fl.oz. (60 - 240 ml)	
60# (27.2 kg) bag Mortar Mix	1.5 - 6 fl.oz. (45 - 175 ml)	

DIVISION 3

Maintenance of Concrete 03 01 00



Table 1B: Thermo-Lube Testing

A "Six Bag" Concrete Mix	with	without
	Thermo-Lube	Thermo-Lube
Water Demand (% by wt)	8.0	9.0
Slump	2.5 in. (64 mm)	2.5 in (64 mm)
Set Time (min.)		
Initial	110	215
Final	155	275
Compressive Strength, psi (MPa)		
3 day	4540 (31.3)	3140 (21.7)
7 day	5020 (34.6)	4130 (28.5)
28 day	6090 (42.0)	5780 (39.9)
3 day 7 day	4540 (31.3) 5020 (34.6)	4130 (28.5)

PRECAUTIONS

• Contains Calcium Chloride. Do not use in areas that will be in contact with steel reinforcement. If color is important, dosage rate should be established and consistently maintained throughout the project.

WARRANTY

NOTICE: Obtain the applicable LIMITED WARRANTY: at www.quikrete.com/product-warranty or send a written request to The Quikrete Companies, LLC, Five Concourse Parkway, Atlanta, GA 30328, USA. Manufactured under the authority of The Quikrete Companies, LLC. © 2018 Quikrete International, Inc.

^{*} Refer to www.quikrete.com for the most current technical data, SDS, and guide specifications