

• TRUSTED QUALITY SINCE 1921 •

RUST-OLEUM®**NO HUNTING PURPLE****DESCRIPTION AND USES**

Rust-Oleum® No Hunting Purple is a durable weather resistant finish formulated for marking trees, fences and property lines. This product is designed for use in states regulated by "No Hunting" paint statutes. NOTE: Paint marks must be readily visible to any person approaching the property and must be no more than 100 feet apart. Each mark must be at least 8" wide and at least 3 feet off the ground and no higher than 5 feet off the ground.

PRODUCTS

| SKU | Description |
|--------|-------------------|
| 270970 | No Hunting Purple |

PRODUCT APPLICATION**PAINTING CONDITIONS**

Use outdoors or in a well ventilated area such as an open garage. Use when the temperature is between 50-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces that will exceed 200°F (93°C) or on galvanized metal. Avoid spraying in very windy, dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent or other suitable cleaning method. Rinse thoroughly with fresh water and allow to fully dry. All surfaces must be dry at time of application. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRIMING

Use 7769 Rusty Metal Primer or 225135 Touch Up Rusty Metal Primer for sound rusted or clean metal before application of a finish coat. 7780 White Clean Primer is best for clean metal but may be used on sound rusted metal as well.

PRODUCT APPLICATION**APPLICATION**

Shake can vigorously for one minute after mixing ball begins to rattle. If missing ball fails to rattle, DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply 2 or more light coats a few minutes apart.

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures and higher humidity. Dries to the touch in 20 minutes, to handle in 1 hour and fully dry in 24 hours. Apply a second coat within 1 hour or after 48 hours.

CLEAN-UP

Wipe off tip before storing. Clean up wet paint with xylene or mineral spirits. Properly discard of empty container. Do not burn or place in home trash compactor.

CLOGGING

If valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not stick pin or other object into the stem.

TECHNICAL DATA

NO HUNTING PURPLE

PHYSICAL PROPERTIES

| | | NO HUNTING PURPLE |
|--|--------|--------------------------------------|
| Resin Type | | Modified Alkyd |
| Pigment Type | | Phthalocyanine Blue, Red Iron Oxides |
| Solvents | | Acetone Naphtha, Xylene |
| MIR | | 0.95 Max |
| Fill Weight | | 12 ounces |
| Recommended Dry Film Thickness (DFT) Per Coat | | 1.0 mil (25 µ) |
| Wet Film to Achieve DFT (unthinned material) | | 4.0 mils (100µ) |
| Practical Coverage at Recommended DFT | | 6-12 sq.ft./can |
| Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity | Touch | 20 minutes |
| | Handle | 1 hour |
| | Recoat | Within 1 hour or after 48 hours |
| Dry Heat Resistance | | 200°F (93°C) |
| Shelf Life | | 5 years |
| Flash Point | | -156°F (-104°C) |
| Safety Information | | For additional information, see SDS |

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.