

• TRUSTED QUALITY SINCE 1921 •



780 ELASTOMERIC ROOF COATING

DESCRIPTION AND USES

Rust-Oleum® 780 Elastomeric Roof Coating provides a high initial reflectivity value of 85%, energy efficiency, long term durability and excellent resistance to weathering and dirt pick-up. This elastomeric roof coating is formulated to meet and/or exceed the standards established in ASTM D 6083. Rust-Oleum 780 Elastomeric Roof Coating waterproofs and weatherproofs metal, weathered single ply membranes as well as smooth surface asphalt built-up and modified bitumen roofing substrates.



PRODUCT FEATURES

- Rain resistant in 2 hours
- Mildew resistant
- Low temperature flexibility to -30°F

PRODUCTS

SKU	780 ELASTOMERIC ROOF COATING
301902	0.9 Gallon
301992	4.75 Gallon Pail
344053	53 Gallon Drum
344007	275 Gallon Tote

COMPANION PRODUCTS

SKU	125 ACRYLIC ROOF PRIMER
345476	4.75 Gallon Pail

SKU	105 MULTI-SURFACE ADHESION PRIMER
324255	0.9 Gallon
326036	4.75 Gallon Pail

SKU	110 WATER-BASED RUST PRIMER
324256	0.9 Gallon
326035	4.75 Gallon Pail

SKU	120 WB ASPHALTIC ROOF PRIMER (Black)
345500	4.75 Gallon Pail

SKU	ELASTOMERIC ROOF PATCH
301898	0.9 Gallon

SKU	ROOF PATCH FABRIC
345646	6"x300'
345647	12"x300'
345648	40"x324'
345649	4"x300'

PRODUCT APPLICATION

SURFACE PREPARATION

All surfaces must be clean and free from dirt, grease, oil, mold, algae, loose granules, loose paint, rust, excess chalk and other foreign matter which could prevent proper adhesion.

PRODUCT APPLICATION (cont.)

SURFACE PREPARATION (cont.)

Use a high pressure wash of at least 2,000 psi. Clean with Rust-Oleum Krud Kutter® Original Cleaner Degreaser, or other suitable cleaner to remove all grease or oily deposits. Seams should be sealed and waterproofed and roof penetrations should be flashed prior to applying the topcoat.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-Approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

METAL: Bare galvanized metal does not require a primer if there is no rust present. Surface must be clean and dry. Steel surfaces must be primed, as does rusty or corroded metal. If the metal panel is not Kynar or previously coated, the surface must be cleaned of all rust as thoroughly as possible by wire brush, power tools or power washed. The surface must be primed with Rust-Oleum 110 Water-Based Rust Primer*.

EPDM, PVC, PIB, TPO AND HYPALON: Must be primed with Rust-Oleum 105 Multi-Surface Adhesion Primer*.

* See primer labels and technical data sheet for correct surface preparation and application procedures.

APPLICATION

Apply only when air, material, and surface temperatures are between 50-100°F (10-38°C) and the relative humidity is below 85%. Mix with a power assisted mechanical mixer before use. Mix until the coating is smooth and consistent. Rust-Oleum 780 Elastomeric Roof Coating can be spray, roll or brush applied. A 3/8" nap roller is recommended if rolling. Airless spray is recommended for optimum results. Good results are generally obtained @ 2,000-3,000 psi at the spray tip.

NOTE: Reinforcement fabric must be used for all repairs or alligatored surfaces.

SPRAY EQUIPMENT RECOMMENDATION

Pumps: Graco® King 45:1, Graco Bulldog 30:1 or gas powered equivalents. Graco GH733, HydraMax 350 or GMax 7900 or other manufacturers' equivalents.

Hose/Pressure: 50'-300' length (depending on spray rig pressure). When using hoses longer than 100', use the next larger hose ID every 50'. Every 50' of hose will reduce the spray pressure of the rig by 10% at the gun tip. i.e. 300' hose - 3/4" (50'/100') to 5/8" (50'/100") to 1/2" (50'/100") to 3/8" (50').

• TRUSTED QUALITY SINCE 1921 •



780 ELASTOMERIC ROOF COATING

PRODUCT APPLICATION (cont.)

SPRAY EQUIPMENT RECOMMENDATION (cont.)

Gun: Graco Contractor Gun, Graco Contractor FTx gun, Graco Silver Plus or equivalent. (Tip extrusions or pole guns can be used).

Tip Type: Heavy Duty RAC Switchtips (GHD-XXX) Gray. Tip sizes are detailed below.

Fan Width (inches)	0.39	0.43	0.47	0.51	0.55	0.59
10"-12"	539	543	547	555	547	559
12"-14"	639	643	647	651	647	659
14"-16"	739	743	747	751	747	
16"-18"	839	843	847	851	847	
Flow Rate	1.60 gpm	1.98 gpm	2.37 gpm	2.79 gpm	2.37 gpm	3.74 gpm

COVERAGE

Metal: Apply 2 coats of Elastomeric 780. Apply 1 gal./100 square feet for the 1st coat and 1 gal./100 square feet for the 2nd coat at 16 wet mils per coat. Over corrugated and irregular metal surfaces, allow for additional surface area by multiplying length x width by 1.15 minimum. Primers may be required on metal roofs. Please contact your Rust-Oleum Representative for more information.

Weathered Single Ply: Prime with Rust-Oleum 105 Multi-Surface Adhesion Primer. 105 Multi-Surface primer applies 300-400 square feet per gallon. After priming, apply 2 coats of Elastomeric 780. Apply 1.5 gal./100 square feet for the 1st coat and 1.5 gal./100 square feet for the 2nd coat at 24 wet mils per coat.

Built-Up/Modified Bitumen: PRIMER OPTIONAL. Prime with Rust-Oleum 125 acrylic primer. Apply 1 coat of 125 acrylic primer at 1 gal./100 square feet at 16 wet mils. Apply 2 coats of Elastomeric 780. Apply 2 gal./100 square feet for the 1st coat and 2 gal./100 square feet for the 2nd coat at 32 wet mils per coat. The surface dictates the actual coverage. The amounts shown are intended as minimum application information.

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Dry times increase at cooler temperatures. Dries to the touch in 2 hours; allow minimum 24 hours recoat. After the first coat, allow to cure until it can support the required foot traffic based on specific job site conditions and roof slope, etc. Environmental or site specific conditions may require variations in cure times.

TINTING

Rust-Oleum 780 Elastomeric Roof Coating can be tinted with up to 2 ounces per gallon with Universal Tint.

PRODUCT APPLICATION (cont.)

CLEAN-UP

Wash tools and equipment with soap and water immediately after use. Wipe up splatters before they dry. Follow equipment manufacturer's directions to clean spray equipment. Properly dispose of all soiled rags and containers.

LIMITATIONS

Application temperature shall be above 50°F. Protect from freezing. Not intended for use in areas subject to vehicular traffic, ponding water and over tar or silicone. Do not apply when rain is imminent.

PERFORMANCE CHARACTERISTICS

ELONGATION

METHOD: ASTM D2370 @ 73°F
 RESULT: +390%

FLEXIBILITY

METHOD: ASTM D522 @ -15°F
 RESULT: Passes ½ inch mandrel bend after 1000 h accelerated weathering

TENSILE STRENGTH

METHOD: ASTM D2370 @ 73°F
 RESULT: 250 PSI

SOLAR REFLECTANCE

METHOD: ASTM C1549
 RESULTS: 0.85 Initial – 0.81 Aged 3 Years

SOLAR REFLECTANCE INDEX (SRI)

METHOD: ASTM C1549
 RESULTS: 107 Initial – 101 Aged 3 Years

• TRUSTED QUALITY SINCE 1921 • 	TECHNICAL DATA	ROC-64
780 ELASTOMERIC ROOF COATING		

PHYSICAL PROPERTIES

		780 ELASTOMERIC ROOF COATING
Resin Type		Water-based Acrylic
Pigment Type		Titanium Dioxide, Zinc Oxide
Solvents		Water
Weight	Per Gallon	12.2 lbs.
	Per Liter	1.46 kg
Solids	By Weight	63%
	By Volume	51%
Volatile Organic Compounds		<10 g/l
Recommended Dry Film Thickness (DFT) per Coat (2 coats required)		Metal - 8.0 mils (200μ) per coat Weathered Single Ply - 12.0 mils (300μ) per coat Built-Up/Modified Bitumen - 16.0 mils (400μ) per coat
Wet Film to Achieve DFT (Unthinned material - 2 coats required)		Metal - 16.0 mils (400μ) per coat Weathered Single Ply - 24.0 mils (600μ) per coat Built-Up/Modified Bitumen - 32.0 mils (800μ) per coat
Practical Coverage		Varies depending on substrate to be coated
Dry Times at 77°F (25°C) and 50% Relative Humidity	Touch	2 hours
	Recoat	24 hours minimum
	Foot Traffic	24 hours
Shelf Life		3 years
Flash Point		>200°F
Safety Information		For additional information, see SDS

Performance Guarantee: Should this product fail due to a defect, unless expressly agreed otherwise by Rust-Oleum in writing, purchaser's sole and exclusive remedy is that Rust-Oleum Corporation will, at its option, either refund to the purchaser the amount paid for the product, or furnish at its expense sufficient product to restore a protective condition to the affected areas. Proof of purchase must be provided. At its discretion, Rust-Oleum may require inspection of the affected areas by a Rust-Oleum representative. Contact Rust-Oleum Product Support at 844-888-0482. Refer to product number and batch code.

NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY RUST-OLEUM, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING BUT NOT LIMITED TO MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Additional extended Material and Labor warranties may be available. Contact your Rust-Oleum Representative for more information.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
 11 Hawthorn Parkway
 Vernon Hills, Illinois 60061

Phone: 844-888-0482
www.rustoleum.com/roofing

Form: GDH-1157
 Rev.: 082219