



CHALKED DECORATIVE GLAZE SPRAYS

DESCRIPTION AND USES

Rust-Oleum® Chalked Decorative Glaze allows you to add a custom antiqued finish to any Chalked painted surface. This semi-transparent Decorative Glaze has good workability allowing you to customize your handcrafted, final look. Chalked Decorative Glazes enhance the details of: • surface texture • wood grain • corners • crevices & more. Ideal for any aerosol or brush Chalked painted surfaces such as wood, laminate, melamine or metal surfaces.

PRODUCTS

SKU	DESCRIPTION (Aerosol)
339835	Aged Glaze
339836	Smoked Glaze

PRODUCT APPLICATION

Use in a well ventilated area such as an open garage. Apply when temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 65% to ensure proper drying. Avoid spraying in very windy, dusty conditions. Cover the surrounding area to protect from spray mist.

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with soap and water and let dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces. Remove any wax by lightly wiping the surface with mineral spirits.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop.

PRODUCT APPLICATION (cont.)

APPLICATION

Allow the Chalked base coat to dry 2 hours before applying Decorative Glaze. Shake can vigorously for one minute after mixing ball begins to rattle. Shake often during use. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Working in small sections hold can upright 10-12" from surface and spray in a steady back-and-forth motion using light coats to achieve desired appearance covering corners, crevices and raised panel sections. While Glaze is still wet, use a cheesecloth or lint free rag, wipe the surface to remove the Chalked Decorative Glaze to desired look. A small amount of mineral spirits on a rag will assist in Glaze removal and customization. On wood surfaces, wipe off in the direction of the wood grain.

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 1 hour and is dry to handle in 2 hours. May be recoated with in an 1 hour or after 24 hours. The finish coat is fully dry in 24 hours. NOTE: Chalked Clear Protective Topcoat can be applied for added protection. Apply according to the label instructions.

DISTRESSING

This paint can be distressed if desired. To distress the surface, lightly sand the surface with fine to medium grit sandpaper or a sanding sponge. Wait 2 hours before sanding or distressing.

CLEAN-UP

Wipe off tip before storing. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.



**CHALKED
DECORATIVE GLAZE SPRAYS**

PHYSICAL PROPERTIES

		CHALKED DECORATIVE GLAZE SPRAYS
Resin Type		Alkyd
Pigment Type		Varies with color
Solvents		Acetone, Mineral Spirit,
MIR		0.80 Max
Weight		12 ounces.
Recommended Dry Film Thickness (DFT) per Coat		1-3 mils (25-75µ)
Dry Times at 77°F (25°C) and 50% Relative Humidity	Touch	1 hour
	Handle	2 hours
	Recoat	Within 1 hour or after 24 hours
Shelf Life		5 years
Flash Point		-141°F (-196°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.