



PRE-MIXED CONCRETE PATCH

◆ The Pro's Choice Since 1936



Sakrete® Pre-Mixed Concrete Patch is a pre-mixed, water-based concrete patch ready to use directly from the container. **KEEP FROM FREEZING.**

Features:

- Premixed – ready to use
- Fills and seals cracks up to 1" (25mm) wide
- Smooths surface defects
- Vertical and horizontal applications
- Interior and exterior uses
- Helps to reduce moisture when filling cracks
- Maintains bond and elasticity through extreme weather conditions
- Easy to apply

Use For:

- Driveways
- Patios
- Walkways
- Curbs
- Stairs
- Masonry

Yield/Coverage:

Container Size	Yield
1 qt (.95 L)	3 ft ² (0.28 m ²) at 1/8" (3.2mm) thickness

NOTE: The yield is approximate and does not allow for waste.

Technical Data:

- 20 - 40 minute skim time
- Hardens in 4 - 6 hours

DIVISION 3

Concrete Topping – 03 53 00

Preparation/Application:

For best results all materials should be stored between 50°F (10°C) and 80°F (27°C) 24 hours prior to installation. **KEEP FROM FREEZING.**

1. Surfaces to be repaired must be sound, dimensionally stable, and clean.
2. Clean all dirt, dust, and loose materials from cracks or rough surfaces with a stiff broom or power washer.
3. Allow to dry prior to application of the Sakrete Pre-Mixed Concrete Patch material.

Mixing:

No mixing is required.

Curing:

1. Product will form a skin in 20 - 40 minutes and harden within 4 - 6 hours.
2. If painting is desired, allow material to cure a minimum of 48 hours (when temperatures are between 65°F and 75°F with no rain in the forecast) before painting.
3. Use a high quality, exterior masonry grade, breathable acrylic latex paint. Curing time will vary based on the thickness of the application.
4. Surface will usually cure in 48 hours but weather and thickness may slow drying. Curing to full depth of cracks may take 5 - 7 days.
5. Keep traffic off the repair area(s) during the curing period. If this cannot be done, sprinkle sand over the repair area to prevent tracking.

Clean Up:

1. Use warm, soapy water for cleaning hands while the product is wet.
2. Dried Pre-Mixed Concrete Repair is insoluble in water. Clean tools and spills before it dries.

Precautions:

Air, mix and substrate temperatures should be between 50°F (10°C) and 80°F (27°C) and no rain in the forecast within 48 hours of application. For applications outside this range of temperatures and conditions, contact Sakrete Technical Service.

- Rubber gloves and goggles are recommended safety equipment.
- Store in tightly sealed original factory containers off the floor in a dry place.
- Do not apply in cracks over 1" (25 mm) wide or surfaces over 1/4" (6.4 mm) thick.
- Colder temperatures or higher humidity conditions will retard set times.
- Do not over trowel.
- Protect from freezing.

NOTE: Proper application and installation of all Sakrete products are the responsibility of the end user.

Safety:

READ and UNDERSTAND the Safety Data Sheet (SDS) before using this product. **WARNING:** Wear protective clothing and equipment. For emergency information, call CHEMTREC at 800-424-9300 or 703-527-3887 (outside USA).

KEEP OUT OF REACH OF CHILDREN.

Limited Product Warranty:

The manufacturer warrants that this product shall be of merchantable quality when used or applied in accordance with the manufacturer's instructions. This product is not warranted as suitable for any purpose other than the general purpose for which it is intended. This warranty runs for one (1) year from the dates the product is purchased. ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ON THIS PRODUCT IS LIMITED TO THE DURATION OF THIS WARRANTY. Liability under this warranty is limited to replacement or defective products or, at the manufacturer's option, refund of the purchase price. CONSEQUENTIAL AND INCIDENTAL DAMAGES ARE NOT RECOVERABLE UNDER THIS WARRANTY.