CC/ECC/ECCU

Column Caps

Column caps provide a strong connection for column-beam combinations.

Material: CC3¼, CC44, CC46, CC48, CC4.62, CC64, CC66, CC68, CC6-71/8, ECC31/4, ECC44, ECC46, ECC48, ECC4.62, ECC64, ECC66, ECC68, ECC6-71/8 - 7 gauge; all others - 3 gauge

Finish: Simpson Strong-Tie gray paint. Some products available in HDG, stainless steel or black powder coat; CCO, ECCO - no coating.

Installation:

- Use all specified fasteners; see General Notes
- Bolt holes shall be a minimum of ¹/₃₂" to a maximum of ¹/₁₆" larger than the bolt diameter (per 2015 NDS, section 12.1.3.2)
- · Contact engineered wood manufacturers for connections that are not through the wide face

Options:

 \bigcirc ° ©

- Straps may be rotated 90° where $W_1 \ge W_2$ (see illustration) and for CC51/4-6.
- For special, custom or rough-cut lumber sizes, provide dimensions. An optional W₂ dimension may be specified. (The W₂ dimension on straps rotated 90° is limited by the W₁ dimension.)
- CCO/ECCO Column cap only (no straps) may be ordered for field-welding to pipe or other columns. CCO/ECCO dimensions are the same as CC/ECC. Weld by Designer.
- CCOB Any two CCOs may be specified for back-to-back welding to create a cross beam connector. Use the table loads; the load is no greater than the lesser element employed.

Codes: See p. 12 for Code Reference Key Chart









Optional ECC with Straps Rotated 90°



Optional CC with Straps Rotated 90°

CC/ECC/ECCU

SIMPSO Strong⁻

Column Caps (cont.)

These products are available with additional corrosion protection. For more information, see p. 15.

For stainless-steel SS fasteners, see p.21.

Model No.	Beam Width (in.)	Dimensions (in.)						Machine Bolts					Allowable Loads (DF/SP)						
		W ₁	W ₂	L					Beam				CC		ECC	ECC EC		Code	CCO/ECCO
				00	F00	FOOL	H ₁	Size		500	ECCU	Post	Uplift Down		Down	Uplift	Down	Ref.	Model No (No Legs)
				CC	ECC	ECCU			CC	ECC			(160)	(100)	(100)	(160)	(100)		
CC3 1/4-4	31⁄8	31⁄4	3%	11	7½	9½	6½	5⁄8	4	2	4	2	3,150	16,980	6,835	3,150	6,835	IBC, FL, LA	CCO3 1/4 ECCO3 1/4
CC3 1/4-6	31⁄8	31⁄4	5½	11	7½	9½	6½	5⁄8	4	2	4	2	3,150	21,485	10,740	3,150	10,740		
CC44	3½	3%	3%	7	5½	6½	4	5⁄8	2	1	2	2	1,850	19,020	7,655	1,850	7,655		CCO4 ECO
CC46	3½	3%	5½	11	8½	91⁄2	6½	5⁄8	4	2	4	2	3,530	24,065	12,030	3,530	12,030		CC04/6 ECC04/6
CC48	3½	3%	7½	11	8½	9½	6½	5⁄8	4	2	4	2	3,530	24,065	16,405	3,530	16,405		
CC4.62-3.62	4 1⁄2	45%	3%	11	8½	9½	6½	5⁄8	4	2	4	2	4,535	23,390	9,845	4,535	9,845		CC04.62 ECC04.6
CC4.62-4.62	4 1⁄2	4%	45%	11	8½	9½	6½	5⁄8	4	2	4	2	4,535	30,070	12,655	4,535	12,655		
CC4.62-5.50	4 1⁄2	4%	5½	11	8½	9½	6½	5⁄8	4	2	4	2	4,535	30,940	15,470	4,535	15,470		
CC5 1/4-4	51⁄8	51⁄4	3%	13	91⁄2	10½	8	3⁄4	4	2	4	2	6,300	26,635	11,210	6,300	11,210		CC05 1/4 ECC05 1/
CC5 1/4-6	51/8	51⁄4	5½	13	91⁄2	10½	8	3⁄4	4	2	4	2	6,500	28,190	17,615	6,500	17,615		
CC5 1/4-8	51/8	51⁄4	7½	13	9½	10½	8	3⁄4	4	2	4	2	6,645	35,235	24,025	6,645	24,025		
CC64	51⁄4, 51⁄2	5½	3%	11	7½	91⁄2	6½	5⁄8	4	2	4	2	5,545	28,585	12,030	5,545	12,030		CC06 ECC06
CC66	51⁄4, 51⁄2	5½	5½	11	7½	91⁄2	6½	5⁄8	4	2	4	2	5,545	33,275	18,905	5,545	18,905		
CC68	51⁄4, 51⁄2	5½	7½	11	91⁄2	9½	6½	5⁄8	4	2	4	2	5,545	37,815	25,780	5,545	25,780		ECC068
CC6-7 1/8	51⁄4, 51⁄2	5½	71⁄8	11	91⁄2	9½	6½	5⁄8	4	2	4	2	5,545	37,815	24,490	5,545	24,490		
CC74	6¾	6%	35⁄8	13	10½	10½	8	3⁄4	4	2	4	2	6,330	33,490	15,355	6,330	15,355		CC07 ECC07
CC76	6¾	61%	5½	13	10½	10½	8	3⁄4	4	2	4	2	6,790	37,125	24,130	6,790	24,130		
CC77	6¾	6%	61%	13	10½	10½	8	3⁄4	4	2	4	2	7,020	48,265	29,615	7,020	29,615		
CC78	6¾	6%	7½	13	10½	10½	8	3⁄4	4	2	4	2	7,145	48,265	32,090	7,145	32,905		
CC7 1/8-4	7	71⁄8	3%	13	10½	10½	8	3⁄4	4	2	4	2	6,360	34,730	18,375	6,360	18,375		CC07 1/8 ECC07 1/
CC7 1/8-6	7	71⁄8	5½	13	10½	10½	8	3⁄4	4	2	4	2	6,825	38,500	28,875	6,825	28,875		
CC7 1/8-7 1/8	7	71⁄8	71⁄8	13	10½	10½	8	3⁄4	4	2	4	2	7,105	57,750	36,750	7,105	36,750		
CC7 1/8-8	7	71⁄8	7½	13	10½	10½	8	3⁄4	4	2	4	2	7,190	52,500	39,375	7,190	39,375		
CC84	7½	7½	35⁄8	13	10½	10½	8	3⁄4	4	2	4	2	6,410	37,210	16,405	6,410	16,405		CCO8 ECCO8
CC86	71⁄2	71⁄2	5½	13	10½	10½	8	3⁄4	4	2	4	2	6,885	41,250	25,780	6,885	25,780		
CC88	7½	71⁄2	7½	13	10½	10½	8	3⁄4	4	2	4	2	7,250	51,565	35,155	7,250	35,155		
CC94	8¾	81%	3%	13	10½	10½	8	3⁄4	4	4	4	2	6,580	47,545	19,905	6,580	19,905		CCO9 ECCO9
CC96	8¾	81%	5½	13	10½	10½	8	3⁄4	4	4	4	2	7,080	48,125	31,280	7,080	31,280		
CC98	8¾	81%	7½	13	10½	10½	8	3⁄4	4	4	4	2	7,455	62,565	42,655	7,455	42,655		
CC106	91⁄4	9½	5½	13	10½	10½	8	3⁄4	4	4	4	2	7,160	52,250	32,655	7,160	32,655		CC010 ECC01

Bases and Caps

1. Uplift loads have been increased for earthquake or wind loading with no further increase allowed. Reduce where other loads govern.

2. Downloads shall be reduced where limited by allowable loads of the post.

3. CC uplift loads do not apply to splice conditions.

4. Splice conditions with CCs must be detailed by the Designer to transfer tension loads between spliced members by means other than the column cap.

5. Column sides are assumed to be aligned in the same vertical plane as the beam sides. CC4.62 models assume a minimum 31/2"-wide post.

6. Structural composite lumber columns have sides that show either the wide face or the edges of the lumber strands/veneers known as the narrow face. Values in the tables reflect installation into the wide face. See technical bulletin T-C-SCLCLM at strongtie.com for load reductions resulting from narrow-face installations.

7. Beam depth must be at least as tall as H_1 .

8. CCO and ECCO welded to a steel column will achieve maximum load listed as CC and ECC. The steel column width shall match the beam width. Weld by Designer.