



**TOUCH 'N TONE  
SPRAY ENAMELS**

**DESCRIPTION AND USES**

Touch 'N tone is an all purpose spray paint designed to provide a durable protective coating that resists fading, chipping and peeling. These sprays apply easily and dry fast to a tough attractive finish. Not for use on galvanized metal.

**PRODUCTS**

SKU	Description
<b>PRIMERS</b>	
252562	Red Primer
254845	Black Primer
55279830	Flat Gray Primer
<b>FINISHES</b>	
55270830	Cherry Red
55271830	Hunter Green
55272830	Canary Yellow
55273830	Aluminum 273
55274830	Gloss White
55275830	Flat Black
55276830	Gloss Black
55277830	Leather Brown
55278830	Royal Blue
55280830	Flat White
55281830	Antique White
55283830	Orange
55284830	Metallic Gold
55285830	Almond
55286830	Clear
55288830	Dove Gray
55289830	Semi-gloss Black
55290830	Dark Blue

**PRODUCT APPLICATION**

**PAINTING CONDITIONS**

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Do not apply to galvanized steel. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

**PRODUCT APPLICATION (cont.)**

**SURFACE PREPARATION**

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper.

**WARNING:** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**APPLICATION**

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-12" from surface and spray in a steady back and forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply 2-3 light coats a few minutes apart to avoid drips and runs. **Do not use near open flame.**

**DRY & RECOAT**

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 20 minutes, dries to handle in 30 minutes and is fully dry in 24 hours.

**CLEAN-UP**

Clean valve immediately after use by turning can upside down and depressing spray button for 3-5 seconds (some paint will be sprayed out, so be careful to not inadvertently spray yourself or other objects). Clean up wet paint with xylene or mineral spirits. Throw away empty can in trash pick-up. Do not burn or place in home trash compactor.

**CLOGGING**

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

**TECHNICAL DATA****TOUCH 'N TONE SPRAY ENAMELS****PHYSICAL PROPERTIES**

Physical Properties		SPRAY ENAMELS
Resin Type		Modified Alkyd
Pigment Type		Varies with color
Solvents		Acetone, Naphtha, Xylene
MIR	Primers & Flats	0.70 Max
	Gloss	0.95 Max
	Metallics	1.25 Max
Fill Weight		10 ounces
Practical Coverage at Recommended DFT (assumes 15% material loss)		Approximately 10-12 sq.ft./can (0.90-1.10 m <sup>2</sup> /can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	10 minutes
	Handle	30 minutes
	Recoat	Within 1 hour or after 24 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		3 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.