

Tintable caulk. Just add paint.

eXact Color[®] Sealant

Tintable Caulk.
Just Add Paint.

sashco
Products That Work

TINTABLE

eXact Color[®] Sealant

A seamless match. Every time.

See back panel for cautions.
9.5 FL. OZ. (280 mL)
(when mixed)



eXact Color® is the easiest and fastest way to create a custom color caulk. This 100% water-based acrylic sealant requires no special tools. Simply mix in any water-based paint or stain to get an exact match. Forget about needing to have 50+ colors on hand. You only need this one to match your job.

Features and Benefits

- ✓ A seamless match, every time
- ✓ Match stains or even metallics! †
- ✓ No special tools required
- ✓ Easy to use water cleanup
- ✓ Super elastic
- ✓ Permanently flexible
- ✓ Powerful adhesion
- ✓ Dripless plunger
- ✓ Interior or exterior
- ✓ Nationally VOC compliant



Where to Use

eXact Color is excellent for use in a variety of areas, including:

Siding	Metals [†]
Cabinets	Plastics
Countertops	Walls & wallpaper
Stained woodwork	Windows & doors
Trim	Moulding
Backsplashes	Baseboards

Where NOT to Use

- Areas of water submersion or frequent, prolonged puddling
- Areas with high foot and/or vehicle traffic (driveways, sidewalks, decks, patios, etc.)
- Roofs exposed to prolonged dampness (use Sashco's Through the Roof!® instead)
- Will not adhere to or is incompatible with Kynar®*, Polypropylene, Waxes, Polyethylene, and Silicone.
- [†] May discolor copper

** Kynar® is a registered trademark of its respective owner.*

Application Basics

Dry Time

Tack free: 30 minutes. Full cure: 4-5 days (depending on temperature and humidity)

Paintable:

Um? Feels like you're missing something here. You mix the paint in, so you shouldn't need to paint it! But, like all Sashco products, you can paint over it.

Clean up / Removal

Soap and water

Application Range

40° to 120°F (4° to 49°C)

Service Range

-30° to 250°F (-34° to 93°C)

How to Use

Before you start:

- Ensure surface is clean
- Application range: 40°F to 120°F
- Protect from water for 48 hours after application
- eXact Color will match paint once it has skinned over in about 4 hours
- Cure time: 4-5 days

Step 1: Cut off the tip of the cartridge above the threading and discard.

Step 2: Using the syringe, draw up 20 mL of paint (or 15 mL of stain) and inject into the top of the cartridge.

Step 3: Screw on cap and shake the cartridge for at least 60 seconds — by hand or in a paint shaker/mixer.

Step 4: Open the thickener, remove the cap from the cartridge, and squeeze the entire contents of the thickener into the cartridge.

Step 5: Replace the cap and vigorously shake the cartridge for at least 60 seconds.

Step 6: Wait at least 30 minutes for the caulk to fully thicken.

Step 7: Remove cap, attach the nozzle, cut it to desired bead size, and apply.

For detailed application instructions and for physical properties, check the eXact Color technical data sheet located at [Sashco.com](https://www.sashco.com).



Cut
Corte

1



Inject
Inyectar

2



Shake
Sacudir

3



Thicken
Espesar

4



Shake
Sacudir

5



Wait
Espere

6



Caulk
Calafatear

7

TYPICAL PROPERTIES:

PROPERTY	VALUE
Joint Size	Maximum 1/2"
Tensile Properties	Recovery at 50% stretch: 100% in 3 minutes Recovery at 100% stretch: 96% in 5 minutes
VOC	36.1 g/L, <1.6% by weight (once the thickener is added to the caulk base)
Viscosity	< 50,000 cps. (caulk base before thickened)
Density of caulk base	8.6 lbs./gal.
Shelf Life	3 years (1 year after mixed)
Sheen	Satin

TEST DATA:

PROPERTY	RESULTS	TEST METHOD
Durability	12.5% movement (10 cycles @ -15°F (-26°C))	ASTM C719
Hardness, Shore A	33 (21-day cure)	ASTM C661
Slump	< 1/8"	ASTM D2202
Solids	56.4% by weight (of caulk base) 54.6% by volume	ASTM C1250
Extrusion Rate	750 g/min (1/8" orifice at 40 psi)	ASTM C603
Freeze-Thaw Stability	3 cycles max at 0°F. No freeze/thaw stability at -15°F. Keep from freezing	ASTM C731
Low Temp. Flexibility	Pass (not artificially weathered)	ASTM C734
Tack-free	Less than 30 minutes	ASTM C679
Cured	4-5 days (dependent on temperature, humidity and bead size)	ASTM C717

**Adhesion-in-peel
Passing Substrates**

Most building materials, including:
Aluminum, Brass, Steel, Anodized
windows, ABS, Lexan®, Acrylic Sheet,
Plexiglass, PVC, Fiberglass, Urethane,
Vinyl, Polycarbonate, Polystyrene,
Nylon, Drywall, Tile, Cinder Block,
Corian®, Wood, Formica®, Glass,
Mortar, Fiber Cement, Stucco, Brick,
Concrete, Stone ASTM C794

SPECIFICATIONS:

- Meets FHA requirements.
- Meets the performance requirements of ASTM C834
- Meets or exceeds Federal Specification TT-S-00230 C

The data reported here are believed to be reliable. No warranty is made concerning the accuracy of or the results obtained from their use.

CAUTION: Avoid contact with eyes and skin. Do not swallow. In case of eye or skin contact, flush thoroughly with water. If irritation persists contact a physician. If swallowed administer two glasses of water and contact a physician immediately.

KEEP OUT OF REACH OF CHILDREN.

LIMITED LIFETIME WARRANTY: Sashco warrants this product will substantially meet published specifications on the date of sale. If it fails to do so, return unused portion with original sales receipt for replacement or refund, at Sashco's sole option. These are purchaser's sole and exclusive remedies for any breach of warranty. Purchaser must determine suitability of product for purchaser's specific needs and assumes all risk associated with its use. Sashco will not be liable for direct or indirect damages.

For a detailed description of the warranty & exclusions, visit sashco.com.



Description	Item #
Contractor Pack	12005
DIY Kit	12030



800-767-5656
sashco.com

Keep up with Sashcoinc on:

