

HCC Holdings, Inc.

4700 West 160th
Cleveland, Ohio 44135

Phone: 800-321-9532
Website: www.Oatey.com



PLASTIC POXY™ Epoxy

Date: August 2017

Unique combination of fast acting epoxy resin and hardener in a single, coextruded stick can be used on many plastics. Comes in a single, easy-to-use package. Made of a pre-measured epoxy resin with a rod of hardener imbedded in the center. Contains a fading blue dye which causes the hardened product to appear off-white when fully mixed. The two-part epoxy compound molds quickly and easily by kneading with the fingers to form a permanent bond in 40 minutes. Adheres to PVC, ABS and CPVC pipe and fittings and many other materials. After curing, it can be drilled, filed, sanded, painted, and machined. Putty-like material can be inserted, shaped, molded, wrapped around or used to build up or repair rigid plastics. Use to repair, rebuild or attach plastic parts. Can be used on applications subject to temperatures up to 250°F for extended periods of time. Do not use on polyethylene, polypropylene and polybutylene.



APPROVALS & LISTINGS

Not applicable.

SPECIFIC USES

Plastic Poxy can be used to seal, mend, bond and repair plastic plumbing, fixtures, appliances and automotive parts.

SPECIFIC APPLICATIONS*

Plastic Poxy can be used to seal, mend, bond and repair plastic plumbing, fixtures, appliances and automotive parts.

*For special applications which may not be covered on this or other Oatey literature, please contact Oatey Technical Services Department by phone 1-800-321-9532, or fax 1-800-321-9535, or visit our technical database web-site at www.Oatey.com.

DIRECTIONS FOR USE

No waste. Cut or break off only amount needed for the job. When mixed, plastic poxy can be molded like putty to desired shapes. Contains a fading blue dye which causes the hardened product to appear off-white when fully mixed. Mixes like putty - hardens like steel. For best results, surfaces should be cleaned of grease and dirt. Smooth surfaces should be roughened by filing or sanding prior to application. Thorough mixing of plastic poxy assures best product performance. Be sure product is mixed until it is uniform in color - not streaky. Mixing in a cold environment may be difficult; warm the product to room temperature before mixing.

This product is not intended for use in structural applications.

- 1) Remove protective end dots and cut or twist off a section of **plastic poxy**.
- 2) Roll and knead **plastic poxy** in palms and between fingers and hands. Fold over repeatedly and continue rolling and kneading until streaks disappear and color is uniform.
- 3) Apply at once to clean, dry surfaces. Force into cracks or holes being repaired. For smooth appearance, hand rub with water or damp cloth before material cures and hardens. Remove any excess material before hardening begins. **Plastic Poxy** will harden and starts to form a strong bond in 35-40 minutes. In 2-3 hours, systems can be put back into service. **Plastic Poxy** can be drilled, sawed, filed, carved, sanded, stained or painted. (When sanding cured **Plastic Poxy** or substrate, use protective eye wear and dust mask.) Full curing will occur in 24 hours. To extend the life of **Plastic Poxy**, recover ends of stick with protective dots and store in original package with cap tightly affixed. If protective dots are missing or damaged, use aluminum foil or plastic kitchen wrap.

PHYSICAL PROPERTIES

Not to be used for specification purposes.

		Testing Method
Lap Shear Tensile Strength on PVC, CPVC, ABS, lbs.:	500-800	ASTM D 1002
Hardness (Shore D) (full cure, 24 hours):	60-70	ASTM D2240
Temperature Limitations, °F:		
Continuous	250°	ASTM D794
Intermittent	300°	ASTM D794
Chemical Resistance:	Resists UL 698 hydrocarbons, ketones, alcohols, esters	
Electrical Resistance:	30,000 mega ohms	ASTM D257
Dielectric Strength, v/mil:	300	ASTM D 149
Compressive Strength (lbs/in ²):	12,000	UL 698
Appearance/color/odor:	2 components in co-extruded mastic form: Blue exterior and off-white interior with mercaptan odor.	

WARNINGS OR CAUTIONS

- Read all cautions and directions carefully before using product.
- **KEEP OUT OF REACH OF CHILDREN.**
- Harmful if swallowed.
- Eye irritant. May irritate sensitive skin.
- Not for use on polyethylene, polybutylene and polypropylene parts such as gasoline tanks.
- Do not use for structural applications.
- Do not use in or on aquariums.

MATERIAL SAFETY INFORMATION

FOR MORE INFORMATION ON THIS PRODUCT, REQUEST SAFETY DATA SHEET (SDS) #7375E

For Delivery By Fax	Call 1-800-321-9535
Internet	See SDS section of www.Oatey.com

SIZE & PACKING

STOCK NUMBER	SIZE	PACKING	WEIGHT/CASE	UPC
25531	4 oz.	24 (2-1 dz.)	8.0 lbs	032628-255319