

# COLD GALVANIZING SPRAY

[Description](#) | [Characteristics](#) | [Applications](#) | [Packaging](#) | [Instructions](#) | [Precautions](#) | [Specifications](#) | [Limited Warranty](#)

## DESCRIPTION:

---

RectorSeal™ Cold Galvanizing Spray provides the protection of hot-dip galvanizing plus the convenience of on the job aerosol application. RectorSeal Cold Galvanizing Spray contains 95% pure zinc and forms a tough, durable, and flexible zinc metal coating that bonds electrochemically with the base metal to protect against rust and corrosion.

[Top of Page](#)

## CHARACTERISTICS:

---

- 95% pure zinc
- Quick drying
- Easy aerosol application
- Use indoors and outdoors
- Electrochemical bond
- Minimal surface preparation
- Stops rust and corrosion on any iron or steel surface
- Permanent, flexible

RectorSeal™ Cold Galvanizing Spray is in full compliance with the following Military Specifications:

MIL-P-26915C  
(USAF)

MIL-P-  
46105  
(MR)

MIL-P-21035B  
(Navy)

[Top of Page](#)

**APPLICATIONS:**

---

Excellent for use on HVAC units to protect exposed sheet metal edges after cutting and installing of duct work and equipment.

May be used indoors or outdoors to prevent and retard rust and corrosion on welded joints, fencing, storage tanks, pipe lines, metal buildings, marine and other similar applications.

[Top of Page](#)

**PACKAGING:**

---

Code	Size	Qty. Per Case	Lbs. per Case	Cu. Ft Per Case
86625	16 oz. Aerosol	12	17	0.63

[Top of Page](#)

**INSTRUCTIONS:**

---

1. Surfaces to be coated must be clean, dry and free of severe rust and loose scale.
2. Shake can well for 1 to 2 minutes before spraying. Repeat often during application.
3. Wear protective eyewear when spraying and point spray nozzle away from face.

4. Hold spray can upright about 10" to 12" from surface and apply thin, even coats with consistent back and forth motion. Allow 15 minutes to dry between coats and 6 hours to dry before top coating.

5. After use, or if spray spatters, turn can upside down and spray to clear nozzle.

**6. Protect surrounding surfaces from overspray.**

For additional technical information, call Toll Free 1-800-231-3345.

[Top of Page](#)

**PRECAUTIONS:**

---

FOR CHEMICAL EMERGENCY, SPILL, LEAK, FIRE, EXPOSURE OR ACCIDENT,

CALL CHEMTREC - DAY OR NIGHT 1-800-424-9300

Contents under pressure. Vapors are extremely flammable. Aerosol may form explosive mixture with air when used. Do not puncture or burn can, expose to heat or ignition sources, or store above 120 degree F. Harmful or fatal if swallowed or inhaled. Can cause skin and eye irritation. Use only with good ventilation. Wear adequate protective gear and clothing. Do not ingest. Avoid breathing vapors and prolonged contact with skin, eyes, and clothing. Wash after handling. Do not use or store near food or feed. Keep can closed when not in use. Do not reuse empty can. Dispose of properly. **KEEP OUT OF REACH OF CHILDREN.**

For additional information, refer to Material Safety Data Sheet.

[Top of Page](#)

**SPECIFICATIONS:**

---

Color

Gray

Spray Pattern - From 12" Distance	2" to 4" Cone
Propellant	Hydrocarbon
Solvent Type	No CFC's or Chlorinated Solvents
Resin	Epoxy Ester
Zinc Dust - Purity	>95%
Particle Size (% less than 45 microns)	100
Film Appearance	Smooth Gray
Dry Time	15 minutes
Cure Time	24 hours

Suggestions and recommendations covering the use of our products are based on our past experience and laboratory findings. However, as we have no control as to the methods and conditions of application, we only assume responsibility for the uniformity of our products within manufacturing tolerances.

[Top of Page](#)

#### **LIMITED WARRANTY:**

---

RectorSeal® makes the Limited Express Warranty that when the instructions for storage and handling of our products are followed we warrant our products to be free from defects. THIS LIMITED EXPRESS WARRANTY IS EXPRESSLY IN LIEU OF ANY OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, AND OF ANY OTHER OBLIGATION ON THE PART OF RECTORSEAL®. The sole remedy for breach of the Limited Express Warranty shall be the refund of the purchase price. All other liability is negated and disclaimed, and RectorSeal® shall not be liable for incidental or consequential damages.

[Top of Page](#)

MANUFACTURED IN U.S.A. BY

RectorSeal®  
2601 Spenwick Drive • Houston, TX 77055 USA  
713-263-8001 • Fax 713-263-7577  
Toll-free 800-231-3345 • Fax 800-441-0051

[Back](#)